

Printing & Packaging Industrial Coatings

Technical Data Sheet

Tinuvin[®] 292



Product Description



Tinuvin[®] 292 is a liquid hindered amine light stabilizer especially developed for coatings. It is an almost pure mixture of the two active ingredients below. It is this combination that keeps the product liquid, unlike the pure diester which tends to solidify, even at room temperature. The efficiency of Tinuvin[®] 292 provides significantly extended lifetime to coatings by minimizing paint defects such as cracking and loss of gloss.

Key Features & Benefits

- Versatile HALS with superior performance in both water- and solvent-based coatings
- Extends usable lifetime of coating by minimizing loss of gloss and cracking
- Excellent compatibility with a wide variety of coatings systems

Chemical Structure

Tinuvin[®] 292 is a) Bis (1, 2, 2, 6, 6-pentamethyl-4-piperidyl) sebacate & b) Methyl 1, 2, 2, 6, 6-pentamethyl-4-piperidyl sebacate



Properties

Typical Characteristics

CAS No:	a) 41556 – 26 – 7 b) 82919 – 37 – 7
Appearance	slightly yellow liquid
Molecular weight	a) 509 b) 370
Dynamic Viscosity at 20 °C	400 cps
Miscibility at 20 °C	Tinuvin [®] 292 is miscible to more than 50% with most commonly used paint solvents. Water solubility is less than 0.01%.

These typical values should not be interpreted as specifications.

Applications

Tinuvin[®] 292 is recommended for applications such as:

- automotive coatings (non-acid catalyzed)
- industrial coatings
- wood stains or do-it-yourself paints
- radiation curable coatings (with no loss of cure speed)

Its high efficiency has been demonstrated in coatings based on a variety of binders such as:

- one- and two-component polyurethanes (water and solvent)
- thermoplastic acrylics (physical drying)
- thermosetting acrylics, alkyds and polyesters
- alkyds (air drying)
- waterborne acrylics
- phenolics, vinylics
- radiation curable acrylics

The dispersion of Tinuvin[®] 292 in waterborne coatings may be facilitated by dilution with a water-miscible solvent such as butylcarbitol.

The performance of Tinuvin[®] 292 can be significantly improved when used in combination with a UV absorber such as recommended below. These synergistic combinations give coatings superior protection against gloss reduction, cracking, blistering, delamination and color change.

The light stabilizers may be added in two-coat automotive finishes to the base and clear coat. However, according to our experience the optimum protection is usually achieved by adding the light stabilizers to the topcoat.

Possible interactions of Tinuvin[®] 292 with paint ingredients such as acid catalysts should be carefully evaluated.

The amount of Tinuvin[®] 292 required for optimum performance should be determined in trials covering a concentration range.

Recommended concentration	Clear coats &	0.5 – 2 %	Tinuvin [®] 292
	One-coat metallic shades:	+ 1 – 3 %	Tinuvin [®] 1130, Tinuvin [®] 384-2, Tinuvin [®] 928, or Tinuvin [®] 400
	One-coat solid shades:	0.5 – 2 %	Tinuvin [®] 292
		alone or in combination with 1 – 3 %	Tinuvin [®] 1130, Tinuvin [®] 384-2, Tinuvin [®] 928, or Tinuvin [®] 400

(concentrations are based on weight percent binder solids)

Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State and Local health and safety regulations, thorough ventilation of the workplace, good skin care and wearing of protective goggles.

Material Safety Data Sheet

All safety information is provided in the Material Safety Data Sheet Tinuvin[®] 292.

Important

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/use, BASF recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS.** In no case shall the descriptions, information, data or designs provided be considered a part of BASF's terms and conditions of sale. Further, the descriptions, designs, data, and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the descriptions, designs, data or information given or results obtained all such being given and accepted at the reader's risk.

Tinuvin is a registered trademark of BASF Group.

© BASF Corporation, 2014



Responsible Care®
Good Chemistry at Work

BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.

For more information on Responsible Care® goto:

U.S.: www.basf.us/responsiblecare_usa

Canada: www.basf.us/responsiblecare_canada

México: www.basf.us/responsiblecare_mexico

U.S & Canada

BASF Corporation

24710 W Eleven Mile Road

Southfield, MI 48033

ph: 1(800) 231-7868

fax:1(800) 392-7429

Email: Custserv_charlotte@basf.com

Email: edtech_info@basf.com

www.basf.us/dpsolutions

Mexico

BASF Mexicana, S.A. de C.V.

Av. Insurgentes Sur # 975

Col. Ciudad de los Deportes

C.P. 03710

Mexico, D.F.

Phone: (52-55) 5325-2756

Fax: (52-55) 5723-3011