



Polyether modified polysiloxane for improved flow and leveling properties and surface smoothness in solvent based and waterborne coatings systems. 100% Active

Description

Borchi® Gol OL 17 is a polyether modified polysiloxane that improves the flow and leveling of solvent based and waterborne coatings systems and improves surface smoothness. It is 100% Active.

Characteristic Data

Color	Hazen: Max. 450	ISO 6271
Refractive index	1.4450 - 1.4490	DIN 51423 (23 °C)
Viscosity	600 - 800 mPa·s	DIN 53015 (23 °C)
Density	1.025 - 1.050 g/cm ³	ISO 2811 (20 °C)
Turbidity	Max. 4 NTU	ISO 7027

Properties

Borchi® Gol OL 17 is an effective flow promoter which also improves surface smoothness by reducing orange peel and preventing the formation of craters. **Borchi® Gol OL 17** may intensify defects caused by over-baking therefore we recommend it should be used primarily in top coats.

Applications

Borchi® Gol OL 17 has good compatibility with a wide variety of binders and is particularly suitable in two component systems based on Desmodur® / Desmophen® resins.

Borchi® Gol OL 17 is water-soluble but its use in such solutions should always be preceded by extensive trials due to limited stability in waterborne binders.

Dosage

The recommended dosage is 0.05 to 0.50 % of the total weight of the formulation depending upon the binder system. The exact dosage should be experimentally determined. Intercoat adhesion failures are not generally observed when used at the recommended levels.

Storage

Protect from the effects of weathering and store at temperatures between 5 and 30 °C. Once opened, containers should be resealed immediately after each removal of the product to avoid exposure to water and atmospheric moisture as much as possible. Under no circumstances should the product be repacked from its original packaging container.



Safety

Please refer to our safety data sheet for information relating to product safety.

Updated: 15.03.2017

Borchers GmbH

Berghausener Str. 100 / 40764 Langenfeld / Telephone: +49 (0) 2173 - 39 26 666
Fax: +49 (0) 2173 - 39 26 999 / Internet: www.borchers.com / E-Mail: info@borchers.com

Our product information is given in good faith but without warranty. This also applies where proprietary rights of third parties are involved. This information does not release the customer from the obligation to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the

products manufactured by the customer on the basis of our technical advice are beyond our control and, therefore, entirely the customer's own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.