

Perkadox AIBN

2,2'-Azodi(isobutyronitrile)

$$\begin{array}{cccc} & & & & \text{CH}_3 \\ & | & & | \\ & | & & | \\ \text{CH}_{\overline{3}} - \text{C} - \text{N} = \text{N} - \text{C} - \text{CH}_3 \\ & | & | & | \\ & \text{CN} & & \text{CN} \end{array}$$

Solid initiator for bulk, solution and suspension polymerization of a wide variety of monomers such as styrene, vinyl chloride, vinylidene, acrylonitrile, acrylates and methacrylates. Generates less aggressive C radicals compared to peroxide initiators, avoiding excessive grafting and form low-molecular weight resins.

CAS number 78-67-1

TSCA status listed on inventory EINECS/ELINCS No. 201-132-3

Molecular weight 164.2

Specifications

Acetone insolubles	≤ 0.1 %
Appearance	White crystalline solid
Assay	≥ 99 %
Color, 2% solution in acetone	≤ 15 Pt-Co / APHA
Iron	≤7 mg/kg
Water	≤ 0.5 %

Characteristics

Bulk density	500-600 kg/m ³
Density, 20 °C	1.110 g/cm ³
Melting point, under decomposition	104 °C

Applications

Perkadox AIBN can be successfully used for bulk, solution, suspension, polymerization of a wide variety of monomers, such as styrene, vinyl chloride, vinylidene, acrylonitrile, acrylates and methacrylates. Perkadox AIBN does not form oxygenated residues and does not cause oxidative degradation of pigmented of dyed polymer systems. For this reason, the color stability or transparent, dyed polymers, such as polymethylmethacrylate, is improved.

Half-life data

The reactivity of an azo initiator is usually given by its half-life (t1/2) at various temperatures. For Perkadox AIBN in chlorobenzene half-life at other temperatures can be calculated by using the equations and constants mentioned below:

0.1 hr	at 101°C (214°F)
1 hr	at 82°C (180°F)
10 hr	at 64°C (147°F)
Formula 1	kd = A·e-Ea/RT
Formula 2	$t^{1/2} = (\ln 2)/kd$
Ea	130.23 kJ/mole
A	2.89E+15 s-1
R	8.3142 J/mole·K
Т	(273.15+°C) K

Thermal stability

Azo initiators are thermally unstable substances, which may undergo self-accelerating decomposition. The lowest temperature at which self-accelerating decomposition of a substance in the original packaging may occur is the Self-Accelerating Decomposition Temperature (SADT). The SADT is determined on the basis of the Heat Accumulation Storage Test.

Method	The Heat Accumulation Storage Test is a recognized test method for the
	determination of the SADT of organic peroxides (see Recommendations on the
	Transport of Dangerous Goods, Manual of Tests and Criteria - United Nations, New
	York and Geneva).

Storage

Due to the relatively unstable nature of azo initiators a loss of quality can be detected over a period of time. To minimize the loss of quality, Nouryon recommends a maximum storage temperature (Ts max.) for each azo initiator.

Ts Max.	25°C (77°F)
Note	When stored under the recommended storage conditions, Perkadox AIBN will remain within the Nouryon specifications for a period of at least three months after delivery.

Packaging and transport

The standard packaging is a cardboard box for 3 x 10 kg initiator. Both packaging and transport meet the international regulations. For the availability of other packed quantities contact your Nouryon representative. Perkadox AIBN is classified as self-reactive solid type C; temperature controlled; Division 4. 1; UN 3234.

Safety and handling

Keep containers tightly closed. Store and handle Perkadox AIBN in a dry well-ventilated place away from sources of heat or ignition and direct sunlight. Never weigh out in the storage room. Avoid contact with reducing agents (e. g. amines), acids, alkalis and heavy metal compounds (e. g. accelerators, driers and metal soaps). Please refer to the Safety Data Sheet (SDS) for further information on the safe storage, use and handling of Perkadox AIBN. This information should be thoroughly reviewed prior to acceptance of this product. The SDS is available at https://polymerchemistry.nouryon.com.

Major decomposition products

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

Perkadox is a registered trademark of Nouryon Chemicals B. V. or affiliates in one or more territories.

Contact Us

Europe, Middle East, India and Africa polymerchemistry.nl@nouryon.com

Asia Pacific

polymerchemistry.ap@nouryon.com

Americas

polymerchemistry.na@nouryon.com

