




Product

IRGALITE BORDEAUX CM

Chemical type	BON (Mn)
CI Constitution No	15860:2
CI Generic Name	PIGMENT RED 52:2



	full shade on white in alkyd melamine paint	full shade on black in alkyd melamine paint	20:80 TiO2 in alkyd melamine paint	5:95 TiO2 in alkyd melamine paint
L*	30.21		46.15	60.22
C*	22.17		41.52	37.67
h	15.01		351.21	343.24
a	21.41		41.03	36.07
b	5.74		-6.34	-10.86

Subindustry specific properties: [Automotive Paints](#) [Decorative Paints](#) [General Industrial Paints](#)

Automotive Paints (Potentially suitable)

Application Suitability :Recommended: Alkyd paint (Polyester, Acrylic)

Auto - Lightfastness

	Full shade	1/3 standard depth	1/25 standard depth
alkyd/melamine paint	7-8	-	4

Auto - Fastness to weathering

	Full shade	1/3 standard depth	1/25 standard depth
alkyd/melamine paint	4	-	2-3

Auto - Resistance to overpainting

stoving paint 30 min 130 °C 5

Auto - Heat resistance

30 min 150 °C 5
10 min 200 °C 3

Auto - Chemical resistance

acid 2
alkali 4